

Trade name: **SIMONA® PE 1000 superlining**

Revision: 05.11.2019

Date of printing: 15.10.2025

**SIMONA® PE 1000
superlining**

Data sheet update	05.11.2019
Density, g/cm ³ , DIN EN ISO 1183	0.93
Tensile modulus of elasticity, MPa, DIN EN ISO 527	680
Yield stress, MPa, DIN EN ISO 527	19
Elongation at break, % , DIN EN ISO 527	> 350
Elongation at yield, % , DIN EN ISO 527	10
Impact strength, kJ/m ² , DIN EN ISO 179	without break
Dielectric strength, kV/mm , DIN IEC 60243-1	44
Sand Slurry, %	80
Shore hardness D (15 s), DIN EN ISO 868	62
Coefficient of dynamic sliding friction	0,1 - 0,2
Mean coefficient of linear thermal expansion, K ⁻¹ , ISO 11359-2	2 x 10 ⁻⁴
Thermal conductivity, W/m * K , DIN EN 12667	0.4
Molar mass	>= 9.000.000
Surface resistivity, Ohm , DIN EN 61340	≥ 10 ¹³
Temperature range, °C	-200 to +80
Comments	FDA food compliance for colours natural, black, grey and dark blue
Food compliance FDA	yes
Physiological safety in accordance with BfR (German Federal Institute for risk valuation)	yes

All specifications are deemed to be approximate values in respect of the specific material and may vary depending on the processing methods used. In general, data specified applies to average values measured on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured by means of pressing, testing is generally performed on sheets with a thickness of 20 mm. Deviations from the values specified are possible if the sheets in this thickness are not available. In the case of backed sheets, all technical specifications relate to the non-backed base sheets. Information presented herein is not necessarily applicable to other products (e.g. pipes, solid rods) of the same material or products

**SIMONA® PE 1000
superlining**

that have undergone downstream processing. Suitability of materials for a specific field of application must be assessed by the party responsible for processing or the end-user. All technical specifications presented herein are designed merely to provide assistance in terms of project planning. They do not constitute a guarantee of specific properties or qualities. All technical specifications and temperature ranges were determined in short-term tests and therefore cannot be used for design work for permanent, long-term use that requires long-term properties. For further information, please contact our Technical Service Centre at tsc@simona.de.